

PEG Low MW (Water Solubility)

1. Analytical Condition

YL 9100 Series

Sample : Polyethylene Glycol MW 1,400 / 106

Mobile Phase : 0.1% TFA 80 / ACN 20

Flow rate : 1 mL/min

Injection : 20 μ l

Column Oven : 40°C

Detector : RID 35 °C

Column : Ultrahydrogel Guard column / Ultrahydrogel 120 * 2

2. Chromatogram

